



## Product Technical Data

### Product Type: 111/6/10

Absorbency (g/g)	
15 Minute Free Swell Capacity (0.9% Saline):	55
15 Minute Free Swell Capacity (DM):	>160
0.3 psi Absorption Under Load (0.9% Saline):	17
0.3 psi Absorption Under Load (DM):	97

Physical Properties	
Colour:	White
Staple Length (mm):	5.8
Moisture Content (%):	10% (Typical)
Count (dtex):	9 (Mean value)
pH (Saline Extract):	5.5 (Mean value)

Other Aspects	
Contamination:	Free of contamination as far as practicable
Packaging:	TAL Standard Bale Specification – wrapped and sealed in polypropylene. Each labelled to show:
	1. Fibre type
	2. Unique bale identification number (traceable through Technical Absorbents quality system)
	3. Bale weight

#### Additional notes

*All tests are carried out in accordance with Technical Absorbents Standard Test Methods which are available upon request. All absorbency specifications are quoted on dry fibre.*

In North America please contact:

#### Contact details

Technical Absorbents Ltd  
1 Moody Lane, Great Coates, Grimsby  
North East Lincolnshire DN31 2SS United Kingdom



**M<sup>2</sup> Polymer Technologies**  
West Dundee, IL USA  
847-836-1393  
www.m2polymer.com